



# MIG 6082



## Standards

AWS 5.14

EN ISO 18274

W. Nr.

ERNiCr-3

Ni 6082

2.4806

## Description & applications

Nickel-based filler metal in solid wire spools for MIG welding of Nickel-Chromium alloys type Inconels 600, 601, Incoloy 800 and Alloy 330. This Nickel-based alloy, frequently called « Alloy 82 », has an excellent behavior from cryogenic conditions up to high temperatures, with a good resistance to creep due to its Niobium content.

It is also used for the welding of 9 % Ni steels in cryogenic and heterogeneous welding in high temperature applications.

## Typical chemical composition (%)

C max 0.05	Mn 3.0	Si 0.5	Cr 20.5	Ni Base	Nb 2.5	S max 0.02	P max 0.02	Fe 3.0
---------------	-----------	-----------	------------	------------	-----------	---------------	---------------	-----------

## Typical mechanical properties of all-weld metal

Rm 660 MPa	Rp 0,2 410 MPa	A5 35%	KV -196°C 60 J
---------------	-------------------	-----------	-------------------

## Operating parameters

### Shielding gas recommendations:

EN ISO 14175 M12 : Argon + 2-3 % CO<sub>2</sub> or Argon + 1-2 % O<sub>2</sub> / 12-18 l/mn



SADEV INOX – 2 Allée des Faisans – 74600 SEYNOD – France

Tel: 04 50 33 70 75 / Fax 04 50 33 70 38 [info@sadevinox.com](mailto:info@sadevinox.com) [www.sadevinox.com](http://www.sadevinox.com)